

NIC**Complex Inorganic Pigments****NIKKEN FAST COLOR**

Product No.	Crystal Structure	CAS No.	C.I.No.	C.I.GN.	PLNo.	Average Particle Size (μm)	Heat Stability ($^{\circ}\text{C}$)	Light Fastness
NF-2800	CoAl_2O_4	1345-16-0	77346	Pigment Blue 28	2-36青289	0.7	1200	excellent
NF-2500	$\text{Co(Al,Cr)}_2\text{O}_4$	68187-11-1	77343	Pigment Blue 36	2-36青290	0.7	1200	excellent
NF-3900	$(\text{Co,Zn,Ni})_2\text{TiO}_4$	68186-85-6	77377	Pigment Green 50	2-36緑77	1.5	900	excellent
NF-5470	$(\text{Ti,Sb,Cr})\text{O}_2$	68186-90-3	77310	Pigment Brown 24	2-36黄226	1.3	1000	excellent
NF-5480	$(\text{Ti,Sb,Cr})\text{O}_2$	68186-90-3	77310	Pigment Brown 24	2-36黄227	0.8	1000	excellent
NF-5495	$(\text{Ti,Sb,Cr})\text{O}_2$	68186-90-3	77310	Pigment Brown 24	2-36黄228	1.0	1000	excellent
NF-5850	$(\text{Ti,Sb,Ni})\text{O}_2$	8007-18-9	77788	Pigment Yellow 53	2-36黄229	1.0	900	excellent
NF-6700	$(\text{Zn,Fe})(\text{Fe,Cr})_2\text{O}_4$	68186-88-9	77503	Pigment Brown 33	2-36茶119	0.7	1000	excellent
NF-6800	ZnFe_2O_4	68187-51-9	77496	Pigment Yellow 119	2-36茶120	0.9	1000	excellent
NF-6900	ZnFe_2O_4	68187-51-9	77496	Pigment Yellow 119	2-36茶121	0.8	1000	excellent
NF-100	$(\text{Co,Fe,Mn})(\text{Fe,Mn})_2\text{O}_4$	68187-94-7	77494	Pigment Black 29	—	1.2	1000	excellent
NF-110	$(\text{Fe,Mn,Cu})(\text{Fe,Mn})\text{O}_4$	68186-94-7	77494	Pigment Black 26	—	1.7	800	excellent
NF-650	$(\text{Co,Fe,Mn})(\text{Fe,Mn,Cr})_2\text{O}_4$	68186-97-0	77502	Pigment Black 27	—	0.8	1400	excellent
NF-710	$(\text{Co,Ni,Fe,Mn})(\text{Fe,Cr,Mn})_2\text{O}_4$	68186-97-0	77502	Pigment Black 27	—	1.2	1400	excellent
NF-767	$(\text{Fe,Cr})_2\text{O}_3$	68909-79-5	77288	Pigment Green 17	—	1.0	1000	excellent
NF-770	$(\text{Fe,Cr})_2\text{O}_3$	68909-79-5	77288	Pigment Green 17	—	1.7	1000	excellent
NF-800	$(\text{Cu,Mn})(\text{Mn,Cr})_2\text{O}_4$	68186-91-4	77428	Pigment Black 28	—	1.0	800	excellent